

1. Product

COMPOREPO B

2. Definition

Mortar concentration based on a mixture of resins and aggregates.

3. General characteristics

- Product easily applied cold.
- Landscape and anti-dust.
- Textured mortar.

4. Technical characteristics

- Dry waste..... 24.8-29.5 %
- Viscosity to 20 °C (Brookfield RVT, spindle n° 6, 100 r.p.m.)31 -46 poises
- pH: 8.6 -10.6

5. Area of application

Sport surfaces

6. Operating instructions

The product is ready for use. Homogenise conveniently before its installation, adding up to 5% of water, only if necessary.

The spreading will be performed on a thin layer at a ratio of 0.8 kg/m² per layer, using a squeegee at a ratio of 0.4 kg/m² per layer. Drying time depends on the ambient temperature and degree of humidity; between 4 and 8 h in dry and sunny weather.

RECOMMENDATIONS:

- Do not apply this product in rainy weather.
- The ambient temperature for its application and curing will range from 10 to 30 °C.
- Do not leave any layer too thick in any case.
- Tools cleaning will be performed using just water, once the work is done.

7. Storage and preservation

The containers will remain sheltered from the weather, in places protected from frost and exposure to strong sunlight. Those temperatures below 5 °C may affect the quality of the product.

Preservation: kept for a year in their original container, tightly closed and undamaged.

8. Supply

The product is supplied in plastic containers of 15 kg.

This information replaces all prior information. The specifications and technical data that appear in this sheet are only guidelines corresponding to laboratory averages. Composan reserves the right to modify them without prior notice and declines any responsibility for their wrongful use.